

Capacity Loss Studies on High Capacity Li-ion Cells for the Orbiter Advanced Hydraulic Power System


Judith A. Jeevarajan

Bradley W. Irlbeck

NASA- JSC

May 9-13, 2004

Judith Jeevarajan/NASA-JSC



- **Introduction**
- **Physical and Electrochemical Characteristics**
- **Performance Evaluation**
 - A. Rate Performance
 - B. Internal Resistance
 - C. Performance at Different Temperatures
- **Safety Evaluation**
 - A. Overcharge
 - B. Overdischarge
 - C. External Short
 - D. Simulated Internal Short
 - E. Heat-to-Vent
 - F. Vibration
 - G. Drop Test
 - H. Vent and Burst Pressure



Orbiter Hydrazine APU Description





Hydrazine APU Used Throughout the Shuttle Program to Power Hydraulic Systems


- Operates During Ascent, On-Orbit Flight Control System Checkout, and Descent
- Converts Chemical Hydrazine Fuel to Shaft Power to Drive a Hydraulic Pump
 - Catalytic Reaction Drives a High Speed Turbine; Speed Reduced to Hyd Pump via a Gearbox

Three Hydraulic Systems Distributed Throughout the Orbiter Power Hyd Actuators

- Variable Displacement, Piston Pump Converts APU Shaft Power to 3000 psi / 69 gpm Fluid Power (120 hp max)
- Hydraulic Power Distributed to 41 End Effectors



Judith Jeevarajan/NASA-JSC




NASA GRC

Boeing – Rocketdyne, Huntington Beach

AEM

AHPS System



Japanese Storage Battery Co.

Boeing – Seattle, Huntington Beach

Crane Naval Surface Warfare Center

Sandia National Labs

Schlumberger

Aeroenvironment

COM DEV Space

NASA JSC ESTA

AEA

SRI

Moog Space Products – Buffalo, NY

Hamilton Sundstrand – Rockford, IL & Windsor Locks, CT


Boeing - Huntington Beach

NASA White Sands


NASA JSC ESTA

NASA MSFC

Judith Jeevarajan/NASA-JSC



Judith Jeevarajan/NASA-JSC




Objective: Determine Long Term Effects of “Storage” Temp & State of Charge (SOC) On Cell Capacity & Resistance

Description: Test Began in April, 2002 When 12 Cells Were Placed in Temperature Chambers and Stored Open Circuit at Various Temperatures and SOC (2 cells per condition). Testing Scheduled to End Sept 04 (~840 days)

Standard Discharge Cycles Performed Periodically to Trend Capacity Loss and Resistance Growth.


Capacity Loss Test Performed at NSWC in Crane, IN



Test Matrix

| Cell Designation | Condition Description | Storage Temp | Storage SOC | Capacity Check |
|------------------|-------------------------------|---|--|---------------------------|
| 112, 113 | Vehicle Between Missions Cold | 5 C (41 F) | 5 – 10% | 30 days |
| 114, 115 | Vehicle Between Missions Nom. | 25 C (77F) | 5 – 10% | 30 days |
| 116, 117 | Orbit Cold | 25 C (77 F) 25 C (77 F) | 5 – 10% 75 – 80% (2.5 mo @ 5-10%, 15 days @ 75-80%, repeat) | 0, 2.5, 3 mo (repeat) |
| 118, 119 | Orbit Nominal | 25 C (77 F) 40 C (104 F) (2.5 mo @ 25C, 15 days @ 40C, repeat) | 5 – 10% 75 – 80% (2.5 mo @ 5-10%, 15 days @ 75-80%, repeat) | 0, 2.5, 3 mo (repeat) |
| 120, 121 | Orbit Hot | 25 C (77 F) 65 C (149 F) (2.5 mo @ 25C, 15 days @ 65C, repeat) | 5 – 10% 75 – 80% (2.5 mo @ 5-10%, 15 days @ 75-80%, repeat) | 0, 2.5, 3 mo (repeat) |
| 122, 125 | Post Landing Hot | 25 C (77 F) 65 C (149 F) (2.5 mo @ 25C, 1 day @ 65C, repeat) | 5 – 10% 75 – 80% (2.95 mo @ 5-10%, 1 day @ 75-80%, repeat) | 0, 2.95, 3 mo (repeat) |

Judith Jeevarajan/NASA-JSC



Standard Discharge Cycle

Standard Discharge Cycle Performed Periodically to Trend Capacity Loss and DC Resistance Growth.


Standard Discharge Cycle Consists of:

- Return to Room Temperature
- Discharge Fully
- Charge Fully to 4.1 VDC
- Discharge at C/2 Constant Current With 2.7 C Pulses at 60, 70, 80, 90 and 100 Minutes (95 amps constant with pulses to 513 amps)
- Upon Reaching 3.0 VDC, Decrease Current to C/10 and Continue Discharge Until Reaching 3.0 VDC
- Charge to Desired SOC
- Return to Desired Storage Temperature

Resistance Calculated Based on dV / dI for the 2.7 C Pulses


- Trends Reported in Following Pages are for the 100 minute Pulse

Judith Jeevarajan/NASA-JSC




Comparison of Standard Capacity Cycles

The first vs last discharge curves for one of the two cells from each of the six storage groups was compared.




Comparison of Discharges Under Ground Storage Conditions at 5 °C & 10% SOC

Cell 112 - Discharge Cycle 1 & 21 (664 days) Comparison
(storage condition: 5 °C & 10% SOC with capacity check every 30 days)





Judith Jeevarajan/NASA-JSC



Comparison of Discharges Under Conditions of Ground Storage at 25 °C & 10% SOC


Cell 114 - Discharge Cycle 1 & 21 (650 days) Comparison
 (storage condition: 25 °C & 10% SOC with capacity check every 30 days)






Comparison of Discharges Under Conditions of On-Orbit at 25 °C & 10%/80% SOC

Cell 116 - Discharge Cycle 1 & 15 (652 days) Comparison
(storage condition: 25 °C & 10% SOC for 2.5 mo, 25 °C & 80% SOC for 0.5 mo with capacity check at 2.5 & 3 mo)




Judith Jeevarajan/NASA-JSC




Comparison of Discharges Under Conditions of On-Orbit at 25 °C/40 °C & 10%/80% SOC

Cell 118 - Discharge Cycle 1 & 15 (653 days) Comparison
(storage condition: 25 °C & 10% SOC for 2.5 mo, 40 °C & 80% SOC for 0.5 mo with capacity check at 2.5 & 3 mo)




Judith Jeevarajan/NASA-JSC




Comparison of Discharges Under Conditions of On-Orbit at 25 °C/65 °C & 10%/80% SOC

Cell 120 - Discharge Cycle 1 & 15 (653 days) Comparison

(storage condition: 25 °C & 10% SOC for 2.5 mo, 65 °C & 80% SOC for 0.5 mo with capacity check at 2.5 & 3 mo)




Judith Jeevarajan/NASA-JSC



Comparison of Discharges Under Conditions of Post Landing at 25 °C/65 °C & 10%/80% SOC

Cell 122 - Discharge Cycle 1 & 15 (651 days) Comparison
(storage condition: 25 °C & 10% SOC for 2.95 mo, 65 °C & 80% SOC for 0.05 mo with capacity check at 2.95 & 3 mo)




Judith Jeevarajan/NASA-JSC



Capacity Loss Data

Quantity of Data Points & Differing Starting Points Make These Results for Absolute Capacity Difficult to Interpret


Crane Calendar Loss Test - Capacity






Quantity of Data Points & Differing Starting Points Make These Results for Absolute Resistance Difficult to Interpret

Crane Calendar Loss Test - Resistance




Judith Jeevarajan/NASA-JSC




Capacity Loss – Ground Storage Conditions

Melco 190 Ah Cell Long Term Capacity Loss (Ground)




Judith Jeevarajan/NASA-JSC




Resistance Growth – Ground Storage Conditions

Melco 190 Ah Cell Long Term Resistance Growth (Ground)




Judith Jeevarajan/NASA-JSC



Capacity Loss – On-Orbit Storage Conditions

Melco 190 Ah Cell Long Term Capacity Loss (Orbit)




Judith Jeevarajan/NASA-JSC




Resistance Growth – On-Orbit Storage Conditions

Melco 190 Ah Cell Long Term Resistance Growth (Orbit)




Judith Jeevarajan/NASA-JSC



Resistance During Standard Capacity Cycle Profile

**(cells with most benign and most extreme storage
conditions)**


Judith Jeevarajan/NASA-JSC




Mission Resistance – Ground Cold Storage

Cell With Most Benign Storage Condition Shows Upward Shifting Curves

Cell 112 Resistance During a Discharge Cycle




Judith Jeevarajan/NASA-JSC




Mission Resistance – Orbit Hot Storage

Cell With Most Extreme Storage Condition Shows Upward Shifting Curves and Rise at End

Cell 121 Resistance During a Discharge Cycle




Judith Jeevarajan/NASA-JSC



Summary of Average Capacity Loss

Average Capacity Loss - JSB 190 Ah Calendar Loss Test at Crane (after 664 days)




Judith Jeevarajan/NASA-JSC



Summary of Average Resistance Growth





Average Resistance Growth - JSB 190 Ah Calendar Loss Test at Crane (after 664 days)



Judith Jeevarajan/NASA-JSC



Results for 190 Ah Cycle Test Conducted at Schlumberger in Rosharon, TX



Judith Jeevarajan/NASA-JSC




Summary of Results

- **Results Excellent for the Orbiter AHPS Application**
- **Mostly Expected Trends with Temperature and State of Charge**
 - Higher Temp and/or Higher SOC Produce More Cell Degradation
- **Cell Capacity Loss Characteristics are Excellent**
- **Cell Resistance Growth Is Greater Than Capacity Loss (% change)**
Apparent Growth is
 - However, Results are Really Magnified Because of the ~~Incredibly~~⁹ Low Initial Cell Resistances
- **Comparison with Sizing Model Used to Reduce Needed Cell Size for AHPS Application from 190 Ah to 120 Ah**
 - Measured Capacity Loss is Less Than Model
 - Measured Resistance Growth is More than Model
 - Overall, 120 Ah Sizing Provides Adequate Margin for the AHPS Application 8 Mission, 30 Cycle, 3 year Requirement

Judith Jeevarajan/NASA-JSC



Acknowledgment



NSWC in Crane, IN.

Judith Jeevarajan/NASA-JSC